

BLAKELY SOKOLOFF TAYLOR**ZAFMAN LLP**A LIMITED LIABILITY PARTNERSHIP
INCLUDING LAW CORPORATIONS

TELEPHONE (310) 207-3800

FACSIMILE (310) 820-5988
(310) 820-5270BSTZ_MAIL@BSTZ.COM
WWW.BSTZ.COM

INTELLECTUAL PROPERTY LAW

12400 WILSHIRE BOULEVARD
SEVENTH FLOOR
LOS ANGELES, CA 90025-1026

OTHER OFFICES

AUSTIN, TX
SUNNYVALE, CA
COSTA MESA, CA
SAN DIEGO / LA JOLLA, CA
PORTLAND / LAKE OSWEGO, OR
SEATTLE / KIRKLAND, WA
DENVER / ENGLEWOOD, CO**FACSIMILE TRANSMITTAL SHEET**

Deliver To: Examiner M. Ruthkosky/Art Group 1745

Company: U.S. PATENT & TRADEMARK OFFICE

Telephone: (703) 872-9725

From: William Hickman

Date: July 19, 2002

Time: _____

Number of Pages: 2 (Including Cover Sheet)

Operator: Nadya Gordon

Our Reference: 003364P020

SUBJECT: Serial No. 09/363,578 - filed 7/29/99**REMARKS:**
Please see the attached sheet per our telephone conference.

CONFIDENTIALITY NOTE: The documents accompanying this facsimile transmission contain information from the law firm of Blakely, Sokoloff, Taylor & Zafman which is confidential or privileged. The information is intended to be for the use of the individual or entity named on this transmission sheet. If you are not the intended recipient, be aware that any disclosure, copying, distribution or use of the contents of this faxed information is prohibited. If you have received this facsimile in error, please notify us by telephone immediately so that we can arrange for the retrieval of the original documents at no cost to you.

If you do not receive all the pages, or if there is any difficulty in receiving, please call: (310) 207-3800 and ask for the operator named above.

VERSION WITH MARKINGS TO SHOW CHANGES MADEIN THE CLAIMS

The claims have been amended as follows.

1. (Five Times Amended) A carbonaceous active material comprising:
at least one crystalline graphite core; and
an amorphous carbon shell coating the outside of the crystalline graphite core
wherein a differential thermal analysis conducted on the carbonaceous active material
in 10°C increments per minute starting from room temperature and proceeding to
1000°C at atmospheric pressure results in the displaying of at least ~~two~~ a first and a
second exothermic peaks overlapping to form shoulders; ~~and the amorphous carbon~~
~~shell coating is derived from an amorphous carbon precursor solution,~~
wherein the first peak corresponds to the crystalline graphite core, and
comprises a first peak temperature lower than 800°C;
wherein the second peak corresponds to the amorphous carbon shell coating,
and comprises a second peak temperature less than and within 200°C of the first peak
temperature.

Please add claim 8 as follows:

8. (New) The carbonaceous active material of claim 1, wherein the second
peak temperature is within 100°C of the first peak temperature.